



2. ACIERS INOXYDABLES

Aciers inoxydables austénitiques forgés selon EN 10222-5

NF A 36-607 (1984)	Symbole DIN 17-440	D	Groupe Matière	WN°	ASTM 182	Groupe Matière	Temp. mini	Temp. maxi
AF Z6 CN18-09	X5 CrNi 18-10	H	11 E 0	1.4301	F 304	2C1	- 196 °C	+ 815 °C
AF Z2 CN18-10	X2 CrNi 19-11	H	10 E 0	1.4306	F 304 L	2C3	- 196 °C	+ 425 °C
AF Z6 CND17-11	X5 CrNiMo 17-12-2	H	14 E 0	1.4401	F 316	2C2	- 196 °C	+ 815 °C
AF Z2 CND17-12	X2 CrNiMo 17-12-2	H	13 E 0	1.4404	F 316 L	2C3	- 196 °C	+ 455 °C

Aciers inoxydables austénitiques moulés selon EN 10213-4

NF A 36-607 (1984)	Symbole DIN 17-445	D	Groupe Matière	WN°	ASTM 351	Groupe Matière	Temp. mini	Temp. maxi
Z6 CN 18.10 N	GX6 CrNi 18-9	H	11 E 0	1.4308	CF8	2C1	- 196 °C	+ 815 °C
	GX2 CrNi 19-11	H	10 E 0	1.4309	CF3	2C1	- 196 °C	+ 425 °C
Z6 CND18.12N	GX6 CrNiMo 19-11-2	H	14 E 0	1.4408	CF8M	2C2	- 196 °C	+ 815 °C
	GX2 CrNiMo 19-11-2	H	13 E 0	1.4409	CF3M	2C2	- 196 °C	+ 455 °C