



5. BRONZES SELON EN 1503-4

EN 1982	DIN	WN°	ASTM	Temp. mini	Temp. maxi
CC 491K	CuSn5Zn5Pb5-C	2.1096	B62 C83600	- 10 °C	+ 260 °C
CB 491K	CuSn5Zn5Pb5-B	2.1097	B30 C83600	- 10 °C	+ 260 °C