



3. FONTES SELON EN 1503-3

Fontes à graphite lamellaire

NF A 32-101 (1965)	NF A 32-101 (1987)	DIN 1691 (1985)	EN 1561 (1997)	WN°	ASTM A 48	Temp. mini	Temp. maxi
FT 20	FGL 200	GG 20	EN-GJL 200	EN-JL-1030	class 20	- 10 °C	+ 200 °C
FT 25	FGL 200	GG 25	EN-GJL 250	EN-JL-1040	class 358	- 10 °C	+ 200 °C

Fontes à graphite sphéroïdale

NF A 32-101 (1987)	DIN 1663 (1977)	EN 1563 (1997)	WN°	ASTM A 536	Temp. mini	Temp. maxi
FGS 500-7	GGG 50	EN-GJS-500-7	EN-JS1050	Gr 60-40-18	- 15 °C	+ 350 °C
FGS 400-15	GGG 40	EN-GJS-400-15	EN-JS1030	Gr 65-45-12	- 15 °C	+ 350 °C
FGS 400-18	GGG 40.3	EN-GJS-400-18	EN-JS1025	Gr 60-40-18	- 20 °C	+ 350 °C